

# Dr. Fixit Fevimate TG



## ONE PACK WATER RESISTANT TILE GROUT

### Description

**Dr. Fixit Fevimate TG** is a fine powder consisting of portland cement, specially selected polymer, properly selected & graded fine fillers, additives and inorganic chemicals. It is used for grouting of tiles, stones, marble joints & edges because it has water repellency properties, excellent adhesion (high bonding strength), soft consistency, workability and seals joint permanently. It is non-shrinking, non-toxic and odourless grout used for sealing of swimming pool & water tank joints as well.

### Standard Compliance / Specification

Meets the requirements of ISO 13007 ; IS 15477; BS EN 13888:2002 standards

### Typical Application

- Dr. Fixit Fevimate TG is used for grouting of ceramic tiles, marbles, natural stones and edges.
- Specially formulated for wet or submerged grouting applications such as swimming pool, bathrooms, toilets, fountains and kitchen areas.
- It can be used for external and internal areas.
- It is used in residential and commercial areas.
- Application up to joint width of 5 mm.
- It is excellent for highly glazed tiles to give a smooth and watertight joints which when set will be both water and mould resistant.

### Features

- **Aesthetics** - Available in two shades.
- **Easy to use** - Easily to mix with water and forms soft consistency paste which is easy to fill the joints.
- **Shrinkage & cracking** - Avoids cracks formation in the joints and also there is negligible shrinkage.
- **Water resistant** - Excellent water-resistance making it beneficial for application in areas immersed under water.
- **Durability & UV resistant** - Excellent UV resistance & durability enables the product use for exterior application.
- **High Strength & abrasion resistant** - High strength & abrasion resistance properties makes it suitable for grouting of toilets & bathrooms.

### Packing

500 g

### Method of Application

---

#### 1 SURFACE PREPARATION

- Surface must be cleaned and should be free from dirt, cured tile adhesive. Remove dust with wire brush & by air blower.
- For exterior grouting application, wet the tiles prior to applying Dr. Fixit Fevimate TG

---

#### 2 MIXING

- Add the grout powder to the mixing water (w:p ratio - 1 : 2.5 by volume) and mix with slow speed drill (250-300 rpm) to a soft & smooth consistency paste.
- If the grout mortar has become too stiff to work, it should be discarded and a new batch should be prepared.

---

#### 3 APPLICATION

- Apply to the tile joints with squeegee, spatula or putty blade. After application flush the surface of tile using a hard rubber float, working diagonally across the grout joints to fill and compact the joints. All excess grout should be removed with the same rubber float without any delay.



- Lesser the quantity of grout left on the face of the tiles while application, the final cleaning will be easier.
- However, it is important to allow the grout to set in the joint and to let it acquire its initial set before any further cleaning. After the initial set of the grout, clean the tile surface with a pad of cheesecloth or towel dampened with minimum quantity of clean and cool water. Rub in a circular motion to further compact the grout.
- The remaining surface grout on the tile can also be cleaned at this time. Scrubbing pad fastened to a float works very well to remove grout from the porous tiles.
- Rebuff the tile surface and grout within 1-2 hours to remove all weep water and grout residue from the surface, which helps to reduce the efflorescence and to control colour variation.

#### 4 CLEANING

- Polish the tiles when the job is complete with a clean dry cloth. Scrubbing the floor with hot water and soap water is the best.
- Due to polymer content, it is advisable to clean the surface immediately after the grouting.

#### Precautions & Limitations

- Do not mix excess water.
- Dr. Fixit Fevimate TG cannot be used where high acid resistance is required because of its cement base.
- The potential for efflorescence is inherent in all cement-based products and it is not to be considered as a manufacturing defect.

#### Technical Information

PROPERTIES	SPECIFICATION	RESULTS
Pot life @ 30°C, minutes		60
Open time, minutes		30
Adjustability, minutes		15 - 20
Initial Set @ R T, hours		2
Final Set @ R T, hours		8
Shear adhesion, KN		7 - 8
Tensile Adhesion, N		800 - 1000
Compressive Strength after dry stage, N/mm <sup>2</sup>	BS EN 12808-3	15 - 20
# Water absorption, %	ASTM C 413	8.3
Shrinkage, %	BS EN 13888	< 0.1

# The water Absorption test results complies with the ANSI 118.6 specification limit

#### Theoretical Coverage

Refer Table for the consumption of Dr. Fixit Fevimate TG for various sizes of tiles



Size of the tile inch x inch	WIDTH OF JOINT			
	2 MM	3 MM	4 MM	5 MM
15x15	9.3	6.2	4.7	3.1
15x30	12.8	8.5	6.4	4.3
10x20	8.7	5.8	4.4	2.9
20x20	12.8	8.5	6.4	4.3
20x30	15.2	10.1	7.6	5.1
25x25	15.8	10.5	7.9	5.3
30x30	18.6	12.4	9.3	6.2

Pls. Add 5 % wastage in Dr. Fixit Fevimate TG consumption mentioned above.

### Shelf Life

Shelf life is 12 months from the date of manufacturing in unopened condition.

Store in a cool & dry place.

### Health & Safety

- Protective clothing, such as gloves and goggles, should be worn.
- Treat any contact to the skin or eyes with fresh water immediately.
- Do not induce vomiting & seek medical
- Assistance immediately.
- Reseal pack after use and ensure product is stored as instructed.

### Other Products Categories available

Dr. Fixit brings you the widest range of Construction Chemicals



Pidilite Industries Limited  
 Construction Chemicals Division  
 Ramkrishna Mandir Road, Post Box No. 17411  
 Andheri (E) Mumbai 400059 INDIA  
 Tel +91-22-2835 7000 • Fax +91-22-2835 7008  
 www.drfixit.co.in • info@drfixit.co.in  
 Dr. Fixit Advice Centre (Toll Free No.) 1800 209 5504

**DISCLAIMER** The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.