

# Dr. Fixit Polyplus CP Admix



## NEW GENERATION INTEGRAL CRYSTALLINE WATERPROOFING AND DURABILITY ENHANCER

### Description

Dr. Fixit Polyplus CP Admix is the new generation single component integral crystalline waterproofing and durability enhancer which produces waterproof and durable concrete with hydrophilic crystals by improving corrosion resistance, reduction in cracks and drastically reducing water permeability under hydrostatic pressure.

Dr. Fixit Polyplus CP Admix is the blend of various active chemicals which reacts with Un-hydrated cement particles in presence of water to form in-soluble needle shape crystals. These needle shape crystals fill the pores and capillary tracks and micro cracks within the concrete and permanently sealed against the penetration of water or liquids from both positive and negative side. The concrete is also protected from deterioration due to harsh environmental conditions.

### Standard compliances and Specification

- Fulfill requirements of ACI-212-3R-10 Chapter 15 and categorized as PRAH - Permeability Reducing Admixture for Hydrostatic Condition.
- Dr Fixit Polyplus CP Admix possess CE approval as per EN 934-2 and all manufacturing unit are also certified with CE approval.

### Areas of Application

#### Waterproofing of reinforced concrete

- Concrete Slabs on grade & below grade
- Water reservoirs & swimming pools
- Tunnels & subways
- Marine structures
- Warehouses & commercial floors
- Cut and cover structures
- Basements & pits
- Sewage & water treatment plants
- Foundations & civil substructures
- Parking structures
- Pre-cast concrete, cast-in-situ and shotcrete applications
- Protect concrete for durability

### Features & Benefits

- Dr. Fixit PolyPlus CP admix contents zero VOC and non toxic in nature.
- Dr. Fixit Polyplus CP Admix compliance with USFDA 170.300 for intended use for aqueous food and beverages.
- Resists extremely high hydrostatic pressure up to 16 Bar.
- Can self-heal crack up to 0.5 mm in presence of moisture.
- Reduces Co-efficient of water permeability by more than 90%.
- Enhances the compressive strength of concrete in long age.
- Reduces drying shrinkage by more than 20%.
- Significantly reduces chloride penetration and improve carbonation resistance.
- Eliminates the risk of alkali silica reaction (ASR) with maximum alkali content of 9%.
- No negative corrosion effect on the reinforcement steel with limited chloride content.
- Protects against sulfate attack.



1317F

Institute for testing and certification  
23

1023-CPR-1317F

EN 934-2:2009+A1:2002

Dr Fixit Polyplus CP Admix  
Crystalline capillary admixture  
Water Resisting Admixture

Chloride content : <0.1% by mass

Alkali content: <10.0 % mass

Compressive strength : ≥85% of control

Conventional dry material content : >99.5%

Air content in fresh concrete : ≤2% by volume

Capillary Absorption (after 90 days curing) : ≤60% by mass.



### Method of Application

- Dr. Fixit Polyplus CP Admix shall mix with freshly mixed concrete at 0.8 - 1% by weight of the cement as per approved mix design quantity. IS 10262-1982 and IS 456-2000 shall adopt to establish concrete mix design to achieve desired performance parameters. Prior mix design trials shall be conducted to ensure cement, plasticizer and Dr. Fixit Polyplus CP Admix compatibility.
- For addition of Dr. Fixit Polyplus CP Admix at centralized ready mix concrete plant, all concrete constituents e.g. Cement, Mineral admixtures, aggregates, and water shall batch and mix thoroughly as per RMC Code of Practice- IS 4926:2003. Prepare Dr. Fixit Polyplus CP Admix powder slurry by mixing 1 part of Dr. Fixit CP Admix with 1.5 part of water by volume ratio. Dose the slurry into ready mix concrete truck mixer. Ensure minimum 3 minutes mixing for uniform distribution of active ingredient of Dr. Fixit Polyplus CP Admix with entire concrete mass. Amount of water which was used for slurry shall deduct while batching the concrete at Ready mix plant.
- For addition of Dr. Fixit Polyplus CP Admix at site, follow same practice of preparing slurry at recommended ratio of 1 part (Dr. Fixit Polyplus CP Admix) and 1.5 part (Water) by volume and mix thoroughly with ready mix concrete by rotating RMC Truck drum mixer for minimum 3 minutes for uniform distribution. Amount of water which was used for slurry shall deduct while batching the concrete at Ready mix plant.
- Placing, compaction & curing of concrete as per IS 456:2000 standard engineering practice or as instructed by the engineer in charge shall follow strictly.
- Please consult Pidilite Technical advisor for specific type of application and performance parameters.

### Precautions & Limitations

- Dr. Fixit Polyplus CP Admix is an effective system for rigid structures only and may not reliably seal movable cracks and joints. However, it can use with other flexible waterproofing system and design for desired waterproofing performance. Please consult Pidilite technical department for clarification and design.
- Setting time of concrete is always affected by chemical ingredients. Set retardation may occur when usage of Dr. Fixit Polyplus CP Admix. The intensity of set retardation is depending upon mix design, curing temperature, cement chemical composition and dosage of Dr. Fixit Polyplus CP Admix in specific volume of concrete. Mix design trial mixes are strongly recommended as per IS 10262 to establish data on workability, setting time and strength development .
- The temperature of the concrete mix should be above 5°C
- For best waterproofing performance, always maintain water to cement/ cementitious ratio within limit mentioned by IS 456-2000

### Technical Information

PHYSICAL PROPERTIES	SPECIFICATION/TEST METHOD	RESULTS
Appearance	Grey powder	
Bulk density	Maximum 1.4 g/cm <sup>3</sup>	
FRESH CONCRETE PROPERTIES (OVER CONTROL)	TEST METHOD	RESULTS
Slump	IS:1199 (Part 2):-2018	No significant change
Density	IS 1199 -(Part 3)-2018	No significant change
setting time	IS:1199 (Part 7): -2018	No significant change
HARDENED CONCRETE MECHANICAL PROPERTIES OVER CONTROL	TEST METHOD	RESULTS
Reduction in Coefficient of Water Permeability at 0.8 % dosage.	BS EN; 12390 (Part 8) :2000 (erstwhile DIN I048)	Reduction by more than 90 % compare to reference concrete
Resist 16 bar Hydrostatic Pressure	BS EN 12390 (Part 8) :2000	Pass - Can resist 16 Bar Hydrostatic Pressure



Self-sealing Cracks in presences of moisture	Customize test method	Heal cracks up to 0.5mm in width
Reduction in Chloride diffusion co-efficient	ASTM C - 1556 - Part 4	Reduction by more than 45 % compare to reference concrete
Reduction in Shrinkage & Cracks	IS 1199:1959 - RA 2018	Reduction by more than 20 %
No detrimental Side effect due to Alkali Silica Reaction (ASR)	Compliance with DIN 18998	Alkali content < 9%
No negative effect on corrosion of steel reinforcement due to chloride content in admixture	Compliance with DIN 18998	Chloride content NIL
Food Grade certification	CFTRI as per USFDA-175.300	Passes

These test results are under lab-controlled atmosphere and actual site results may vary. Please contact technical team for finalization of dosage and properties. We always recommend trials on site before regular production.

**Dosage**

0.8% - 1% by weight of cement.

**Packing**

20 kg Bag

**Shelf Life**

12 months from the date of manufacturing when stored in a cool & dry place, away from direct sunlight.

**Health & Safety**

- Dr. Fixit Polyplus CP Admix is a dry powder that becomes reactive when mixed with water or human perspiration.
- Avoid contact with skin or eyes.
- Avoid breathing dust. Wear long sleeves, safety goggles and impervious gloves.
- Refer the Material Safety Data Sheet for this product.

**Other Products Categories available**

Dr. Fixit brings you the widest range of Construction Chemicals



Pidilite Industries Limited  
 Construction Chemicals Division  
 Ramkrishna Mandir Road, Post Box No. 17411  
 Andheri (E) Mumbai 400059 INDIA  
 Tel +91-22-2835 7000 • Fax +91-22-2835 7008  
 www.drfixit.co.in • info.drfixit@pidilite.com  
 Dr. Fixit Advice Centre (Toll Free No.) 1800 209 5504

**DISCLAIMER** The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.