

Dr. Fixit Triflex Metal Primer



SINGLE COMPONENT PRIMER FOR METAL AND RUSTY SUBSTRATES

Description

Dr. Fixit Triflex Metal Primer is single-component quickly re-coatable metal primer with a high-grade alkyd resin base.

Areas of Application

Dr. Fixit Triflex Metal Primer is used as a primer on various metals and rusty substrates prior to application of Dr. Fixit Triflex range of PMMA products.

Features & Benefits

- Fast-drying
- Rust-inhibiting
- Low viscosity
- Lead- and chromate-free

Method of Application

- Dr. Fixit Triflex Metal Primer can be applied at substrate and ambient temperatures between +5 °C and +35 °C. The relative humidity must not exceed 85%.

Preparation of the substrate

- The substrate must be dry and free of loose particles, grease and oil. For best adhesion results, remove rust, rust scale, mill scale and unstable old coatings. Where blasting is impractical, loose rust, rust scale and old paint layers should be removed with a scraper or wire brush. Stable old coatings should be roughened for better adhesion. Adhesion with stable old coatings must be tested on a case-by-case basis. During application, the surface temperature must be at least 3 °C above dew point. Below that, a separating film of moisture can form on the surface.

Instructions for use

- Before applying the product, stir or shake the contents until homogeneous. Apply a thin layer of Dr. Fixit Triflex Metal Primer using a short-pile roller or a brush consumption of 80-100 ml/m². Make sure the application layer is not too thick. Once the Dr. Fixit Triflex Metal Primer has fully hardened, it can be further processed.

Technical Properties

PROPERTIES	TYPICAL VALUES
Colour	Light Grey
Density	1.1-1.2 g / cc
Viscosity	1500-2500 cps
Recoating time @ 30°C	45 mins

Recommended Coverage

Minimum 80-100 ml/m² on a smooth, even surface in one coat.

The specified consumptions apply only to smooth, even surfaces. Special allowances must be made for unevenness, roughness and porosity etc.

Packaging

Dr. Fixit Triflex Metal Primer - 3 litre metal can (Light Grey colour).



Shelf Life & Storage

Shelf life is 24 months. To be stored unopened and unmixed in a cool, dry place above freezing. Keep container away from direct sunlight when in storage and on the construction site. Storage temperature: 8°C-35°C.

Safety & Handling

During application wear protective clothing, gloves and eye goggles during application. Avoid product to contact eyes and skin. Skin Contact - Wash immediately with plenty of clean water. Eye contact - In the event of eye contact splash plenty of clean water immediately and seek medical advice.

Other Products Categories available

Dr. Fixit brings you the widest range of Construction Chemicals



Pidilite Industries Limited

Construction Chemicals Division
 Ramkrishna Mandir Road, Post Box No. 17411
 Andheri (E) Mumbai 400059 INDIA
 Tel +91-22-2835 7000 • Fax +91-22-2835 7008
 www.drfixit.co.in • info.drfixit@pidilite.com
 Dr. Fixit Advice Centre (Toll Free No.) 1800 209 5504

DISCLAIMER The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.